

○ APPLICATIONS

PVC, polycarbonate, polyester, polyamide, duroplastics and painted surfaces.

○ FEATURES

Mono-component ink with opaque finish and excellent coverage. Ink conforms to legislation 91/155/EWG.

Excellent resistance to chemical products, mechanical action and hands sweat.

○ PROCESSING

Mix and strongly dilute the ink by using the PLBUV2/R/A thinner in the measure of max. 10-20%.

CAUTION!

Excessive dilution generates a loss of the covering power, smudges and an imperfect detachment of the ink from the pad. An insufficient dilution causes problems of drawing the ink from the cliché, printing repeatability and dripping of the ink with a consequent decline of the printing quality.

○ DRYING AND HARDENING

Drying to be carried out with UV equipment between 500 and 2000 mj/cm².

The ink is completely hardened after 24 hours.

○ COLOUR RANGE

Consult the COMEC ITALIA color chart of matt hues that includes a selection of 24 standard colors plus 3 three-color shades.

All of the color shades can be mixed with each other. Upon request:

- special sample colors
- metallic gold and silver shades ready for use.

○ ADDITIVES

PLBUV2/R/A thinner.

○ PRESERVATION

Lasts approximately 6/8 months from the date of production.

Conditions for preservation: the package must be sealed tight and put in a dry and cool place.

CAUTION: ESSENTIAL NOTES!

The information and data contained in this sheet and those provided by Comec Italia by any means are purely indicative, since the conditions of the products' utilization are beyond our control.

We recommend that you make some preliminary trials in order to ascertain the selected product's suitability for the material and the work conditions prior to starting a new production run.

The use of any product remains entirely under the responsibility of the customer.

The manufacturer reserves the right to make changes it deems necessary at any time.

*Total or partial reproduction of this sheet is prohibited without the written authorization of **Comec Italia srl**.*